



# CHAPCO® QDP PLUS

## Quick-Set Deep Patch



### PRODUCT DATA

# SURFACE PREPARATION

#### 1. PRODUCT NAME

CHAPCO® QDP PLUS Quick-Set Deep Patch

#### 2. MANUFACTURER

H.B. Fuller Construction Products Inc.  
1105 South Frontenac Street  
Aurora, IL 60504-6451 U.S.A.  
800-552-6225 Office  
www.chapco-adhesive.com

#### 3. DESCRIPTION

CHAPCO QDP PLUS Quick-Set Deep Patch is a cement-based underlayment designed specifically for deep fills, ramping, and leveling concrete and plywood subfloors (dry areas only) from featheredge up to 1½" (38 mm) in a single application, up to 5" with proper aggregate. Can be applied with steel trowel, float and/or screed to produce a smooth, level surface. CHAPCO QDP PLUS cures to a walkable surface in approximately 60 minutes.

#### Key Benefits and Features

- Calcium aluminate technology for rapid strength development
- Interior/exterior use (mix with CHAPCO ADDITIVE for exterior use)
- Featheredge to 1½" in a single application, up to 5" with proper aggregate
- Fast-set – allows for quick installation
- High bond and compressive strengths
- Provides smooth surface ready to accept flooring
- Self-drying formula

#### Packaging

25 lb. Moisture Resistant Bag (11.34 kg)  
Product #70-5689-3069

#### Recommended Substrates

- Concrete
- Burnished concrete\*
- Cement terrazzo
- Epoxy terrazzo\*
- Epoxy coatings\*
- Ceramic tile (including porcelain and quarry tile)\*
- Exterior grade plywood, APA grade trademarked exterior plywood, C-C (plugged) or better (no additive needed)
- Gypsum substrates\* -- minimum tensile bond strength 72 psi (0.5 MPa)

\*Requires priming with CHAPCO MP Multi-Purpose Primer

#### Coverage

Thickness	1/8" (3mm)	1/4" (6 mm)	1/2" (12 mm)	1" (25 mm)
Approximate Coverage per 25 lb. (11.34 kg) Bag	30-32 ft <sup>2</sup> (2.8 - 3.0 m <sup>2</sup> )	15-16 ft <sup>2</sup> (1.4 - 1.5 m <sup>2</sup> )	7-8 ft <sup>2</sup> (0.65 - 0.74 m <sup>2</sup> )	3.5-4 ft <sup>2</sup> (0.33 - 0.37 m <sup>2</sup> )

#### Storage/Shelf Life

Store in a cool dry area away from direct sunlight. Maximum shelf life is 6 months from date of manufacture in unopened bag.

#### Limitations

Do not apply when the temperature is at or expected to be below 50°F (10°C). Not for use in conditions of hydrostatic pressure or excessive moisture. Not recommended for use as a wear surface. Not for use over sealed concrete, resilient

flooring, strip wood flooring, tempered hardboard, particle board or lauan plywood.

#### Cautions

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about guidelines for the proper use and application of the covered CHAPCO under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

#### 4. TECHNICAL DATA

CHAPCO QDP PLUS	
Physical State	Dry powder
Color	Gray
28 Day Compressive Strength	4,200 psi
Working Time	15-20 minutes
Walkable Hardness	Approximately 60 minutes
Install Floor Covering*	1-1½ hours

\*Flooring material installation is dependent on thickness, drying conditions and type of flooring.

#### 5. INSTALLATION INSTRUCTIONS

##### Preparation of Surfaces

All surfaces must be structurally sound, dry and free from oil, grease, dust, loose or peeling paint, sealers, floor finishes, curing compounds or any contaminant that would prevent a good bond. **For installation over cutback adhesive, remove adhesive by scraping until all that remains is a thin transparent layer of adhesive residue.** Concrete and cementitious substrates must be fully cured and free of any hydrostatic pressure or excessive moisture. All surface protrusions must be removed by sanding, scraping or chipping. Minimum tensile bond strength of 72 psi (0.5 MPa) is required. Substrate temperature should be a minimum of 43°F (6°C) during application and air temperature maintained above 50° (10°C). DO NOT cover existing building expansion or control joints. Remove all dust by vacuuming. For surfaces that require priming, use CHAPCO MP Multi-Purpose Primer per label instructions. Not recommended for use over expansion or control joints.

CHAPCO QDP PLUS can be installed over new or moist concrete with RH of 95% or 15 lbs per 1,000 ft<sup>2</sup> per 24 hours. For moisture sensitive floor coverings refer to the finished floor manufacturer's specifications on moisture limitations. Remediation of excessive moisture conditions must be addressed prior to the installation of CHAPCO QDP PLUS. To reduce moisture vapor emissions to an acceptable level, use CHAPCO'S DEFENDER Moisture Vapor Barrier (see product data sheet for details).

##### Mixing Instructions

Slowly add the entire bag of CHAPCO QDP PLUS to 2 – 2½ quarts (1.9 - 2.4 L) of clean, cool water and mix with a high power drill (650 RPM). Avoid breathing dust and contact with eyes and skin. Mix thoroughly to a smooth, lump-free consistency. Smaller amounts may be hand mixed, 3½ parts CHAPCO QDP PLUS to 1 part water.



## Application Instructions

Immediately after mixing, apply CHAPCO QDP PLUS onto the flooring substrate. Using a trowel or screed, work the material into the substrate and then finish with a steel trowel to a smooth level surface. Working time is approximately 15-20 minutes, depending on ambient temperature and relative humidity. High temperatures and low humidity will shorten working time. CHAPCO QDP PLUS can be applied from a featheredge up to 1½" (38 mm) depth in a single application. Pour up to 3" with two applications. Wait until walkable hardness between coats. Prime first coat, if waiting 6 hours or more. Up to 5" thickness may be placed with the addition of aggregate (well-graded, washed, and dried at ½" or ¼"). To ensure proper bond, all aggregate and substrate must be completely coated with the underlayment mixture. Do not use sand. For further information, please contact your CHAPCO representative.

## Drying Time

CHAPCO QDP PLUS achieves walkable hardness in approximately 60 minutes. Installation of most floor covering materials can be applied within 1 to 1½ hours. When hot, dry or windy weather conditions exist, CHAPCO QDP PLUS should be protected to avoid rapid water loss during curing period. CHAPCO QDP PLUS is cement-based, and all general rules of concrete work should be observed to achieve maximum results. Never use forced air to accelerate the drying of CHAPCO cement-based products. For best results, always test performance of finished floor systems prior to application.

## Clean-up

While material is still fresh, clean tools, hands and equipment with warm, soapy water.

## 6. AVAILABILITY AND COST

To locate a distributor in your area, please contact:

phone: 800-832-9002

website: [www.chapco-adhesive.com](http://www.chapco-adhesive.com)

## 7. WARRANTY

H.B. Fuller Construction Products Inc. offers a limited warranty on this product when installed in accordance with H.B. Fuller Construction Products Inc. printed specifications. Ask your sales associate or call 800-832-9002 for a copy of the limited warranty.

## 8. MAINTENANCE

Not applicable.

## 9. TECHNICAL ASSISTANCE

Information is available by calling the Technical Support Hotline:

Toll-free: 800-832-9023

## Technical and Safety Literature:

To acquire technical and safety literature, please call 800-832-9023.

## 10. FILING SYSTEM

Division 3 - Concrete

Division 9 - Finishes



H.B. Fuller Construction Products Inc.  
1105 South Frontenac Street  
Aurora, IL 60504  
PH 800.832.9002  
[www.chapco-adhesive.com](http://www.chapco-adhesive.com)